



TECHNICAL SPECIFICATIONS

AB-613

SPECIFICATION ASTM D1330-85

Grade 1 or 2

POLYMER: Styrene-Butadiene (SBR)

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.65
D2240	HARDNESS (Shore A)	80
D412	TENSILE (psi)	700 min.
	ELONGATION (%)	150 min.
D395B	COMPRESSION SET	22 hrs @ 70°C 40% max.
D573	HEAT AGING	94 hrs @ 70°C Changed Tensile: -25% max. Elongation: -25% max.
Temperature Range (general guideline):		-20° to 200°F (-29° to 93°C)
Maximum pieces per roll: 2		
Minimum piece length: 10'		
Width tolerance: -0 /+ 1"		
Length tolerance: ± 10%		
Durometer tolerance: +5 -10 max.		
Material is within RMA commercial gauge tolerances.		

Please ensure the product meets your application specification prior to order placement.

